

# MasterInject<sup>®</sup> 1315

Low viscosity epoxy resin with long potlife for crack injection

## DESCRIPTION

**MasterInject 1315** is a low viscosity epoxy resin based crack injection resin system long mixed potlife designed for sealing cracks in concrete and restoring its structural integrity.

## RECOMMENDED USES

- Stabilised cracks in structural members
- Sealing of cracks from 0.1mm to 10mm
- Unfilled voids behind tiles or stone facades
- Bonding of steel plates to concrete
- Rapid structural repair of concrete
- Grouting dowels

## FEATURES AND BENEFITS

- **Solvent free** -Low VOC and non-shrink
- **Pre-proportioned packaging** - No job site errors
- **Low viscosity** - Easy to inject into fine cracks
- **High bond strength to concrete** -Can restore the structural integrity of the concrete
- **Cures hard at low temperatures** -Wide application range
- **High heat deflection temperature** – Suitable for high ambient temperature environments
- Can be applied for Wet and Damp Substrates

## PROPERTIES

Mixed resin and hardener only			
Viscosity (25°C)	<500 cps		
Compressive Strength (ASTM C579)	65 MPa @ 1 day		
	70 MPa @ 7 days		
Flexural strength (ASTM C 6319 part 3)	45 MPa @ 1 day		
	55 MPa @ 7 Days		
Tensile strength(ASTMD638) 7days	18 MPa		
Pot life	50 minutes @ 25°C		
	30 minutes @ 40°C		
Slant shear bond strength (ASTM C 882 @ 7 days)	>18 MPa (Concrete failure)		
Bond strength	>2.5 MPa (concrete failure)		
Tack free time	6.5 hours @ 25°C		
Meets the requirements of ASTM C881 Type 1 & 4 Grade 1 Class B & C			
	<b>Part A</b>	<b>Part B</b>	<b>Mixed</b>
<b>Supply Form</b>	Liquid	Liquid	Liquid

<b>Colour</b>	Clear	Amber	Pale Yellow
<b>Mix Ratio</b>	77:23 pbw		
<b>Density (Mixed)</b>	1.05kg/L		
<b>Application Temperature</b>	15°C - 35°C		

## APPLICATION

### Surface preparation

Remove all grease, oil, dust, residual curing compound, mould release agent or other contaminant that could impair adhesion of the injection ports. The injection ports should be applied over 6-10mm diameter holes drilled at least 50-75mm into the concrete element. For deeper penetration deeper holes should be considered. Use **MasterBrace ADH 2200** to adhere the injection ports over the holes ensuring that the adhesive does not block the drilled holes. Allow the **MasterBrace ADH 2200** to cure before injecting . The ports should follow the crack at intervals of 500mm or a maximum of 1m centres. Inject from the lowest point or furthest point towards the centre checking for resin coming out of the next hole along. For detailed instructions on crack injection ask you Master Builders Solutions representative for the “**MasterInject** guide to crack injection”.

### Mixing

Proportion part kits accurately mixing only what can be used in less than 30 minutes. Thoroughly stir Part A, add Part B and blend thoroughly using a slow speed mixer fitted with a suitable paddle.

## CURING

Cure time will vary depending on the ambient temperature, quantity mixed and placed. **MasterInject 1315** will have fully cured after 7 days at 23°C.

## ESTIMATING DATA

Usage will depend on the injection pressure and the size of the cracks and is impossible to estimate.

## PACKAGING

**MasterInject 1315** comes in 1.08 kg and 4.32 kg pack sizes.

## SHELF LIFE

**MasterInject 1315** can be stored in tightly closed original containers for 12 months at moderate temperature.

# MasterInject® 1315

## PRECAUTIONS

It is highly recommended to use necessary PPE (Gloves, mask etc.) during installation of the product. In case of Incidents of direct inhalation, causing dizziness/giddiness, loss of consciousness, contact with eyes etc, seek immediate medical advice. The requirements may vary depending on the application areas. Please ensure to have proper ventilation while working in confined areas. Contact Master Builders Solutions

representative in case you need further details or refer to the material safety datasheet of the product to know more.

MasterInject 1315/04/05/2022

® = registered trademark of a MBCC Group member in many countries of the world

### STATEMENT OF RESPONSIBILITY (Disclaimer)

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions India Private Limited  
Registered office: Plot No D-126,  
TTC Industrial Area, MIDC,  
Shiravane, Navi Mumbai - 400706,  
Maharashtra, India  
Tel: +91 8657906776  
E-mail: [Construction-india@mbcc-group.com](mailto:Construction-india@mbcc-group.com)  
[www.master-builders-solutions.com/en-in](http://www.master-builders-solutions.com/en-in)

